

Comment on “Orbital Order, Structural Transition and Superconductivity in Iron Pnictides” by Yanagi *et al.*

Hiroshi KONTANI¹, and Seiichiro ONARI²

¹ Department of Physics, Nagoya University and JST, TRIP, Furo-cho, Nagoya 464-8602, Japan.

² Department of Applied Physics, Nagoya University and JST, TRIP, Furo-cho, Nagoya 464-8602, Japan.

(Dated: April 11, 2011)

Recently, Yanagi *et al.* in Ref. [1] claimed that the development of ferro-orbital fluctuations induced by the “orthorhombic phonon” is the origin of high- T_c superconductivity and softening of the shear modulus C_{66} in iron pnictides. In this comment, we explain that the orthorhombic-phonon model has serious difficulty in explaining high- T_c . The reason is that the orthorhombic-phonon is “acoustic” with the energy $\omega_{\mathbf{q}} \propto |\mathbf{q}|$, although the authors in Ref. [1] treated it as optical phonon ($\omega_o = 0.02\text{eV}$) inconsistently.

In Refs. [2–4], we have shown that weak electron-phonon (e -ph) interaction due to Fe-ion optical phonons with energy $\omega_o \sim 0.02\text{eV}$ produces strong antiferro-orbital fluctuations. For example, Fig. 1 (a) depicts $\mathbf{q} = 0$ and $\mathbf{q} = (\pi, 0)$ Fe-ion optical modes. The derived orbital fluctuations induce the s -wave superconductivity without sign reversal (s_{++} -wave). A rough estimation for the transition temperature is

$$T_c \sim \omega_o \exp(-1/\alpha\lambda), \quad (1)$$

where $\lambda \sim 0.2$ is the dimensionless e -ph coupling constant, and $\alpha \gg 1$ is the enhancement factor for the orbital susceptibility, $\alpha \sim \chi^c(\mathbf{q})/\chi^0(\mathbf{q})$, given by the RPA [3]. Since $\alpha\lambda \gtrsim 1$ in iron pnictides, we conclude that high- T_c of order $\sim 50\text{K}$ can be realized.

In Ref. [1], Yanagi *et al.* had added an “orthorhombic phonon” to the model proposed in Refs. [2–4], and claimed that the enhancement of ferro-orbital fluctuations due to this phonon is the origin of high- T_c . However, in contrast to the treatment in Ref. [1], the orthorhombic phonon is “acoustic” [5], which is given by the transverse mode in Fig. 1 (b), and is also included in the longitudinal mode in (c). The acoustic phonon energy $\omega_{\mathbf{q}} \propto |\mathbf{q}|$ vanishes at $\mathbf{q} = 0$ shown in Fig. 1 (d). Therefore, the enhancement of ferro-orbital fluctuations cannot give high- T_c since the prefactor in eq. (1) vanishes at $\mathbf{q} = 0$.

In fact, it is hard to expect that T_c exceeds $\omega_{\mathbf{q}}$ since the phonon-mediated interaction $g_{\mathbf{q}}(\omega) \propto (\omega^2 - \omega_{\mathbf{q}}^2)^{-1}$ changes from attractive to repulsive at $\omega = \omega_{\mathbf{q}}$, as shown in Fig. 1 (e) [6]. Although authors in Ref. [1] explained high- T_c by putting $\omega_{\mathbf{q}} = 0.02\text{eV}$ even at $\mathbf{q} = 0$ erroneously, the orthorhombic-phonon model has serious difficulty in explaining high- T_c in iron pnictides in reality.

Next, we discuss the softening in the shear modulus above the orthorhombic structure transition temperature T_S [7, 8]. Recently, Yoshizawa *et al.* [9] had per-




FIG. 1: (a) Displacements $\mathbf{u}$ due to in-plane Fe-ion optical modes; $\mathbf{q} = 0$ -mode and $\mathbf{q} = (\pi, 0)$ -mode. Motions of As-ions are not shown. (b) A transverse acoustic mode ($\mathbf{q} \parallel (\hat{x} + \hat{y}) \perp \mathbf{u}$). (c) A longitudinal acoustic mode ($\mathbf{q} \parallel \mathbf{u} \parallel \hat{x}$). (d) Energies of optical and acoustic phonons. (e) Energy dependence of the phonon-mediated pairing interaction.

formed systematic measurement in $\text{Ba}(\text{Fe}_{1-x}\text{Co}_x)_2\text{As}_2$ for $x = 0 \sim 0.225$, and found that C_{66} shows the largest softening in both under- and over-doped systems. C_{66} corresponds to the orthorhombic deformation below T_S , and the structure transition (C_{66} -softening) is expected to be induced by the ferro-orbital order (fluctuations). However, inconsistently with the claim in Ref. [1], the orbital order obtained in the orthorhombic-phonon model is “incommensurate” [10], which is inconsistent with the abovementioned experimental results. Therefore, the origin of the orthorhombic structure transition and large C_{66} -softening is still unclear.

In summary, the orthorhombic-phonon model proposed by Ref. [1] has serious difficulty in explaining high- T_c in iron pnictides. The reason is that the “orthorhombic-phonon” is acoustic phonon, although the authors treated it as optical phonon inadequately.

Note added in proof: Recently, the present authors found that the ferro-orbital fluctuations for the C_{66} -

softening is induced by the two-orbital process with respect to the antiferro-orbital fluctuations [12].

-
- [1] Y. Yanagi, Y. Yamakawa, N. Adachi and Y. Ōno: J. Phys. Soc. Jpn. **79** (2010) 123707 [arXiv:1010.0129].
 - [2] H. Kontani and S. Onari, Phys. Rev. Lett. **104**, 157001 (2010).
 - [3] T. Saito, S. Onari, and H. Kontani, Phys. Rev. B **82**, 144510 (2010).
 - [4] S. Onari and H. Kontani, arXiv:1009.3882
 - [5] The origin of $\mathbf{q} \approx 0$ orbital fluctuations in Ref. [1] is the e -ph interaction due to the “orthorhombic mode”, which is proportional to

$$(|xz\rangle\langle xz| - |yz\rangle\langle yz|) \cdot \mathbf{u}_{\text{ortho}}, \quad (2)$$

where xz, yz represent the d -orbitals; x - and y -axes are along the nearest Fe-Fe directions. Equation (2) is produced by As-ion deformations shown by red dashed lines in Figs 1 (b) and (c). However, these deformations are not involved in the $\mathbf{q} = 0$ optical modes since they violate the translational symmetry of the Fe_2As_2 unit cell.

All the $\mathbf{q} = 0$ optical phonons in the FeAs-plane (normal coordinates for the Fe_2As_2 cluster) are given as A_{1g} (As; out-of-plane), B_{1g} (Fe; out-of-plane), $2E_g$ (Fe+As; in-plane), and A_{2u} (Fe+As; out-of-plane) and E_u (Fe+As; in-plane); see S.C. Zhao *et al.*, Supercond. Sci. Technol.

- 22**, 015017 (2009). It is easy to check that any of them do not give eq. (2). (B_{2g} mode is required to produce eq. (2) while it is absent in the $\mathbf{q} = 0$ optical modes.) Therefore, the $\mathbf{q} = 0$ “orthorhombic mode” is purely acoustic, contrary to the statement in Ref. [1].
- [6] In contrast, the sign of the spin-fluctuation propagator $\chi_{\mathbf{q}}(\omega) \propto (1 + \xi^2(\mathbf{q} - \mathbf{Q})^2 - i\omega/\omega_{\text{sf}})^{-1}$ [see SCR theory or Millis-Monien-Pines model] does not change at $\omega \sim \omega_{\text{sf}}$. In case of spin-fluctuation-mediated superconductivity, $T_c \sim \omega_{\text{sf}}$ is possible.
 - [7] R.M. Fernandes, L. H. VanBebber, S. Bhattacharya, P. Chandra, V. Keppens, D. Mandrus, M.A. McGuire, B.C. Sales, A.S. Sefat, and J. Schmalian, Phys. Rev. Lett. **105**, 157003 (2010)
 - [8] M. Yoshizawa, R. Kamiya, R. Onodera, Y. Nakanishi, K. Kihou, H. Eisaki, and C. H. Lee, arXiv:1008.1479.
 - [9] M. Yoshizawa *et al.*, private communication.
 - [10] In Fig. 3(c) of Ref. [1], $\chi^c(\mathbf{q}, 0)$ due to the orthorhombic phonon has an incommensurate peak with momentum $\mathbf{q} \approx (0.35\pi, 0)$, so the words “ferro-orbital order” in Fig. 4(a) should be corrected to “incommensurate orbital order”. In case of the five-orbital model in Ref. [11], we find that $\chi^c(\mathbf{q}, 0)$ due to the orthorhombic phonon takes the maximum at $\mathbf{q} \approx (\pi, 0)$ due to the nesting, while it is hardly enhanced at $\mathbf{q} = 0$.
 - [11] K. Kuroki, S. Onari, R. Arita, H. Usui, Y. Tanaka, H. Kontani, and H. Aoki, Phys. Rev. Lett. **101**, 087004 (2008).
 - [12] H. Kontani, T. Saito, and S. Onari, arXiv:1103.3360.